

# Product Information Sheet



## Black PVC Modular C3 Membrane (Cooley)

**PIN # 1128**

### Item Description

47Mil 11' & 13' wide smooth back x custom length

### product Number

MP-450206 MP-451206

### Product Information

Developed for RPW Associates, Inc and manufactured in partnership with Cooley in 2019 while maintaining all the key benefits of our standard white C3 PVC-KEE membranes, our black PVC-KEE is the perfect solutions for those areas where a PVC membrane is optimal but white isn't an appropriate solution. The matte finish is perfect for airports and other high traffic areas where glare must be kept at a minimum. The Black C3 is formulated with Cooley's patented ultra-high-strength Aramid yarns added along the fastener edge to provide maximum tensile strength and puncture resistance where it counts the most. C3 is a proprietary formulation blending DuPont™ KEE (ketone ethylene ester) and PVC. This unique blend offers superior UV performance and the highest chemical resistance in a single-ply roofing product.

### Method of Application:

The Black Cooley C3 membrane is used in mechanically attached and fully adhered roofing systems in new construction, reroofing and recover (retrofit) for Modular applications. It may also be used as flexible membrane flashings for walls, curbs, etc, when installing Cooley C3 smooth back membrane roofing systems. The system must be installed over acceptable roof insulation or other suitable substrate.

### Storage:

- Store away from sources of punctures and physical damage.
- Assure that structural decking will support the loads incurred by material when stored on rooftop. The deck load limitations should be specified by the project designer.

### Precautions:

- Refer to Safety Data Sheets (SDS) for safety information.
- Exercise caution when lifting, moving, transporting, storing or handling membrane rolls to avoid sources of punctures and possible physical damage.

# Product Information Sheet



## Typical Properties:

Base Fabric	Standard	Metric
Base Fabric Weight	3.41 oz / yd <sup>2</sup>	116 g / m <sup>2</sup>
Fiber/Style	Polyester - Aramid / Knit	

Coated Fabric	Standard	Metric
Thickness, overall	47 (+/- 4) mils	1.2 (+/- 0.10) mm
Thickness, over scrim (min)	16 mils	0.41 mm
Coating Type	PVC / KEE	

Material Properties	ASTM Test Methods	Standard	Metric
Tensile Strength, Grab (Warp / Fill)	D751A	270 / 240 lbs	1,200 / 1,070 N
Tensile Elongation (Warp / Fill)	D751A	15% / 15%	
Tear Strength, Tongue (Warp / Fill)	D5884	45 / 45 lbs	200 / 200 N
Properties After Oven Aging (retained)			
Tensile Strength, Grab	D573	90%	
Tensile Elongation	D573	90%	
Puncture Strength (FTMS 101C)	Method 2031	300 lbs	1,330 N
Hydrostatic Resistance	D751	350 psi	2.4 MPa
Abrasion Resistance (H18 / 1 kg)	D3884	2,000 cycles	
Ply Adhesion (at Aramid edge)	D751	25 lbs / 2 in	111 N / 5 cm
Ozone Resistance (no cracks)	D1149	Pass	
Water Absorption	D471	< 3 %	
Dimensional Stability (1 hr / 100°C)	D1204	< 1 %	
Properties After 2 yr Weathering (retained)			
Tensile Strength, Grab	G90 / cycle 1	90%	
Tensile Elongation	G90 / cycle 1	90%	
Low Temp	D2136	-40°F	-40°C